

weber.floor 4936

Silica sand (0.3 – 0.8 mm) for scatter-coats

Low-fine particle, graded and silica sand for scattering over fresh epoxy resins

Fields of application

For sprinkling fresh epoxy resin primers up to saturation.

Description

weber.floor 4936 is a factory-mixed, low-fine particle, graded and oven-dried quartz sand.

Main features

- tested slip resistance (OS-8 System according to German standard)
- very uniform grit range
- grain size 0.3 - 0.8 mm
- hardness grade 7 according to Mohs scale
- low fines
- high acid resistance
- bright and uniform colour

Quality control

weber.floor 4936 is subject to a regular quality control.

General notes

- The filling degrees indicated here refer to a material and substrate temperature of +20°C.
- The filling ratio of reactive resins with silica sand depends on prevailing temperatures.
- All characteristics mentioned in this data sheet relating to waiting times between operations or substrate preparation, are mentioned in the technical data sheets of the reactive resins (primers and coatings).

Substrate preparation

- Refer to the technical data sheets of the epoxy resin primers **weber.floor 4710/4712**.

Working instructions

- If possible, scatter **weber.floor 4936** vertically onto the fresh epoxy resin primer.
- After curing (next day) sweep off and vacuum off any loose sand.

Practical information

Storage:

The product can be stored at least 5 years, if stored cool and dry.

Packagings

Type	Sales unit	Number / euro-pallet
Paper bag	25 kg	40 bags

The information in this technical data sheet is based on our current knowledge and experience at the time of printing. However, they do not guarantee in the legal sense.